



UCTCF-5000

POLYUREA CRACK FILLER

UNE MARQUE SIKA
A SIKA BRAND

DESCRIPTION

UCTCF-5000 polyurea crack filler is two parts, high penetration, fast setting, hybrid polyurea for repairing and re-building damaged concrete. The product is a 1:1 mixing ratio, that is 98% solids and VOC compliant. UCTCF-5000 can be used to set anchor bolts, repair damaged control joints, fill spalling, and rebuild vertical curbing and steps. Sand or gravel can be added to extend the volume of the material and acts as filler for repairing large spalls, holes and cracks.

PRIMARY APPLICATIONS

- Garage floors
- Aircraft hangar floors
- Commercial freezer repairs
- Industrial shop floors
- Car washes or wash bays
- Bridges/street repairs
- Staircase repair

ADVANTAGES

- Application temperature between -5 C to 38 C
- Product cures in 10 minutes @ 22 C with excellent adhesion
- Self-leveling and self-priming
- Ready to service in 10 to 20 minutes
- Highly chemical resistant
- Excellent for industrial floor repairs subject to forklift traffic and harsh conditions

TECHNICAL SPECIFICATIONS AND MECHANICAL DATA

PACKAGING	4 Gallon kit	RECOMMENDED FULL CURE	30-60 minutes @ 25°C
MIX RATIO BY VOLUME	1:1	SOLIDS BY WEIGHT (%)	100%
IDEAL TEMPERATURE	24 - 27°C	SHELF LIFE	12 months unopened
POT LIFE @ 25° C	2-3 minutes	VOC G/L	397
RECOMMENDED THINNER	DO NOT DILUTE		

PROPERTIES @ 23°C (73°F) 50% R.H.

TENSILE STRENGTH	4500-4800 psi	COMPRESSIVE STRENGTH	5600 psi
ELONGATION AT BREAK	6-8%	HARDNESS, SHORE D	68-72



UCTCF-5000

POLYUREA CRACK FILLER

UNE MARQUE SIKA
A SIKA BRAND

SURFACE PREPARATION

The surface to be coated must be well primed. Remove dust, laitance, grease, oils, dirt, impregnating agents, foreign matter, any previous coatings, and disintegrated substances by mechanical means such as shot-blasting (BLASTRAC) or any other approved method to obtain an ICRI-CSP 3-4 profile. The compressive strength of the concrete must be at least 25 MPa (3625 lbs/in²) after 28 days and the tensile strength at least 1.5 MPa (218 lbs/in²).

MIXING

Mix each component separately. Pour component B into component A using the proper mixing ratio. Mix both components for not more than 30 seconds. Only prepare quantity that may be applied during pot life.

APPLICATION

Pour the UCTCF-5000 into the cracks and allow material to overflow slightly. Once hardened, grind the surplus with a grinder equipped with a diamond wheel.

CLEANING

Clean all application equipment with the recommended cleaner (SCT-0001). Once the product has hardened, it can only be removed by mechanical means. In case of skin contact, wash thoroughly with warm soapy water.

RESTRICTIONS

- Do not apply at temperatures below 10 ° C / 50 ° F or above 30 ° C / 86 ° F.
- The relative humidity of the surrounding work environment during the application of the coating and throughout the curing process should not exceed 85%.
- Substrate temperature must be 3 ° C (5.5 ° F) above dew point measured.
- Humidity content of substrate must be <4% when coating is applied.
- Do not apply on porous surfaces where a transfer of humidity may occur during the application.
- The application of this coating on an interior or exterior substrate without a moisture barrier is at risk of detachment (by hydrostatic pressure).
- Protect the coating from all sources of moisture for a period of 48 hours.

HEALTH AND SAFETY

In case of skin contact, wash with water and soap. In case of eye contact, immediately rinse with water for at least 15 minutes. Consult with a doctor. For respiratory problems, transport victim to fresh air. Remove contaminated clothes and clean before reuse. Components A and B contain toxic ingredients. Prolonged contact of this product with the skin is susceptible to provoke an irritation. Avoid eye contact. Contact with may cause serious burns. Avoid breathing vapors release from this



UCTCF-5000

POLYUREA CRACK FILLER

UNE MARQUE SIKA
A SIKA BRAND

product. This product is a strong sensitizer. Wear safety glasses and chemical resistant gloves. A breathing apparatus filtering organic vapors approved by the NIOSH/MSHA is recommended. Predict suitable ventilation. Consult the material safety data sheet for further information.

IMPORTANT NOTICE

The information and recommendations contained in this document are based on reliable test results according to CTM Coatings. The data mentioned are specific to the material indicated. If used in combination with other materials, the results may be different. It is the responsibility of the user to validate the information therein and to test the product before using it. CTM Coatings assumes no legal responsibility for the results obtained in such cases. CTM Coatings assumes no legal responsibility for any direct, indirect, consequential, economic or any other damages except to replace the product or to reimbursement the purchase price, as set out in the purchase contract.